

Schoorstraat 26/A 2200 Heist-op-den-Berg TEL: 0032-15/40.90.60 www.buvetex.be

Bliss

Home & Contract, Industry collection

Technical data sheet

ТҮРЕ	artificial leather (eco-friendly coated fabric)	
APPLICATION	seat upholstery	
DESIGN NAMES	-	

GENERAL		
Composition surface		100%PVC
Composition back cloth		100% recycled PL (GRS)
Roll width		>137cm (+5)
Weight (ASTM D751)		675gr/m²
Thickness		1.00mm (+/-0.1)
TESTS	<u>METHOD</u>	RESULT / U.M.
Crocking resistance dry-wet	CFFA 7	pass
UV resistance	ATM G153 / AATCC	>=7 blue wool scale
Cold resistance	CFFA 6a, C°	no cracking, -32
Resistance to blocking	CFFA 4	2 max
Martindale abrasion	UNI EN ISO 12947-2 (rubs)	>300.000 cycles
Minimum adhesion	ASTM D751(N/25.4mM)	>=27MD/CMD
Tensile	ASTM D751 (N)	410MD/310CMD
Migration	UNI EN ISO 23999	no migration
Burning and melting behavior	ECE 118 R03 annex 6+7+8	pass
REPELLENCY AND CLEANABILITY		
Antimicrobial		pass
Mildew resistance (ASTM G2I)		pass
Odor test VDA 270 C2/C3		<3
Bleach cleanable, alcohol cleanable		pass
CLEANING INSTRUCTIONS		



Schoorstraat 26/A 2200 Heist-op-den-Berg TEL: 0032-15/40.90.60 www.buvetex.be

Superior cleanability. Water and neutral soap. Cleanable with alcohol and resistant to bleach.

BIOCOMPATIBILITY

REACH & RoHS compliant

No PCP, phthalate free, no PBTs, no Ozone depleting chemicals, no BPA, Bromine free, no HFRs

Compliant to Stockholm covention on POPs

Formaldehyde <10 (mg/kg) UNI EN ISO 14184-1

Skin safe UNI EN ISO 10993-10

SUSTAINABILITY

Standard: 100% recycled knitted PL backing (PET bottles)

81% sustainable content: use of bio-based plasticisers (soya bean oil) + bio-attributed PVC resins (biomass)



Production powered by renewable hydro-electricity. Low VOC water-based formulations. Reuse of waste in production process, rest redirected out of landfill.

REMARKS

*** VERY INTENSIVE USE***

Slight color differences between production batches can occur. The test results only apply to the samples tested. Buvetex can't be kept liable for inappropriate use of the artificial leather.